

## 4. Finish Painting: ✓

Inside: Two coats of Tnemec #272 topox. Recommended coverage - 140 sq. ft. per gallon for a dry film thickness of 5.4. Total dry mil thickness - 12.0 mils. Tint first coat to insure proper coverage.

Outside: Two coats of Tnemec Gloss, Recommended coverage rate - 320 sq. ft. per gallon for a dry film thickness of 2.0 mils. Tint first coat to insure proper coverage. Color to be selected by engineer.

## D. AREAS:

Inside: 4,700 sq. ft.

Outside: 11,250 sq. ft.

## E. THICKNESS TEST:

Dry mil thicknesses to be tested with Mikrotest Gage.

200 M Gal DEW T & T

For

Orono, Minnesota

**PITTSBURGH-DES MOINES STEEL COMPANY**  
**ENGINEERS - MANUFACTURERS - CONTRACTORS**

Dwg PI (Sh't 2)

Date \_\_\_\_\_

Contract 20683